

PrintaSleeve

Printasleeve Ltd, Higher Street, West Chinnock,
Crewkerne, Somerset, TA18 7QA

Email: info@printasleeve.com Tel: 01935 881516, Fax: 01935 881314
www.printasleeve.com

PB and **PG** are braided from monofilaments of Polyester making them very resistant to abrasion

- Ideal for covering single or multi-installation cables
- Often used for extra protection on hoses or plastic piping
- Expansion rate of 2:1
- Sleeving will fit over connectors etc. before returning to its supplied diameter
- Can be supplied in coils, reels, mini-packs or cut to length

Material Characteristics:

Filament Diameter:	0.22mm
Melting Point:	250°C
Maximum Working Temperature:	150°C
Short-Term Peak Temperature:	220°C
Minimum Working Temperature:	-50°C
Limited Oxygen Index:	33
Fume Toxicity:	passes CEI 754-1&2 (Halogen Free)
Fume Opacity:	passes NF C20452 (Polymer)
Chemical Resistance:	Unaffected by most chemicals
RoHS:	Fully Compliant
Standard Colours:	Black (PB) and Grey (PG) <i>(For more colours, please refer to PC3X)</i>



Reference	Application Range (mm)	Coil Size(m)	Spool size (m)
PB03	1.0 to 5.0	100	500
PB04	2.0 to 7.0	100	500
PB05	3.0 to 9.0	100	500
PB06	4.0 to 11.0	100	500
PB08	5.0 to 13.0	100	300
PB10	7.0 to 15.0	100	300
PB12	8.0 to 17.0	50	300
PB15	10.0 to 20.0	50	300
PB20	14.0 to 26.0	25	200
PB25	18.0 to 34.0	25	200
PB30	20.0 to 40.0	25	150
PB40	30.0 to 50.0	25	100
PB50	40.0 to 66.0	25	100
PB60	57.0 to 80.0	25	100
PB75	65.0 to 98.0	25	100
PB100	85.0 to 140.0	25	50

Reference	Application Range (mm)	Coil Size(m)	Spool size (m)
PG03	1.0 to 5.0	100	500
PG04	2.0 to 7.0	100	500
PG05	3.0 to 9.0	100	500
PG06	4.0 to 11.0	100	500
PG08	5.0 to 13.0	100	300
PG10	7.0 to 15.0	100	300
PG12	8.0 to 17.0	50	300
PG15	10.0 to 20.0	50	300
PG20	14.0 to 26.0	25	200
PG25	18.0 to 34.0	25	200
PG30	20.0 to 40.0	25	150
PG40	30.0 to 50.0	25	100
PG50	40.0 to 66.0	25	100

Can also be supplied in reels, midi-reels or 5m mini-packs, with or without dispenser boxes

Other grades of braiding are available. Please refer to **PC3X** and **Type P**, or contact us to discuss other alternative braiding solutions